

## TerraGrid 110

## Geogrids

TerraGrid geogrids are made up of woven high tenacity polyester and coated with a polyvinyl chloride (PVC) coating. TerraGrid geogrids are non-biodegradable and resistant to most soil chemicals, acids, and alkalis with a pH range of 3 to 12. TerraGrid 110 is manufactured to meet or exceed the following machine direction roll value requirements.

Tensile Properties Ultimate Strength Ultimate Strain at Failure Creep Reduced Strength	ASTM D 6637 ASTM D 6637 ASTM D 5262	Tult εult TI	English <u>lbs/ft</u> 10,250 17.0% 6,500	<u>kN/m</u>
Design Strength Properties Creep Reduction Factor Aging / Durability Reduction Factor Installation Damage Reduction Factor Soil Type 1 100mm Max, 30mm D50, PI<6 Soil Type 2 20mm Max, 0.7mm D50, PI<6 Soil Type 3 20mm Max, 0.1-0.5mm D50, PI<20	NCMA '97 NCMA '97 NCMA '97 RFID RFID RFID	RFCR RFD	1.57 1.10 1.40 1.05 1.05	1.57 1.10 1.40 1.05 1.05
Long Term Design Strength  Tult / (RFID for Soil Type 1 x RFD x RFCR)  Tult / (RFID for Soil Type 2 x RFD x RFCR)  Tult / (RFID for Soil Type 3 x RFD x RFCR)	NCMA '97	LTDS LTDS LTDS	<u>lbs/ft</u> 4,089 5,653 5,653	<u>kN/m</u> 59.7 82.5 82.5
Design Interaction Properties Coefficient of Interaction Soil Type 1 100mm Max, 30mm D50, PI<6 Soil Type 2 20mm Max, 0.7mm D50, PI<6 Soil Type 3 20mm Max, 0.1-0.5mm D50, PI<20	GRI – GG5	CI CI	0.75 0.85 0.80	0.75 0.85 0.80
Coefficient of Direct Sliding Soil Type 1 100mm Max, 30mm D50, PI<6 Soil Type 2 20mm Max, 0.7mm D50, PI<6 Soil Type 3 20mm Max, 0.1-0.5mm D50, PI<20	ASTM D-5321	Cds Cds Cds	0.65 0.90 0.85	0.65 0.90 0.85
Physical Properties Aperture Roll Size			.79in x .98 in 12 ft x 150 ft	21mm x 25mm 3.66 m x 45.7m